

# HDT THROW N' GO BERM

Secondary Spill Containment Berms



## KEY FEATURES

- No assembly required
- Walls lay flat when not in use
- Fastest deployment in the industry for portable spill containment systems (simply throw and go)
- Can be driven on at any angle
- 2' wall availability permits smaller footprint
- In the event of a spill, walls automatically rise to create a catch basin
- Optional built-in track mats help prevent damage to the berm
- Berm contains no working parts which would malfunction
- Meets EPA regulations for spill containment
- Heavy-duty 30 oz fabric is appropriate for water, hydrocarbons, and most chemicals
- Easily emptied through 3/4" drains
- Available in tan, green, and black

Specifications	10' x 10'	10' x 20'	12' x 36'	14' x 54'
<b>Dimensions</b>				
6" Wall	12' 1" x 12' 1"	12' 1" x 22' 1"	14' 1" x 38' 1"	16' 1" x 56' 1"
12" Wall	13' 6" x 13' 6"	13' 6" x 23' 6"	15' 6" x 39' 6"	17' 6" x 57' 6"
18" Wall	14' 10" x 14' 10"	14' 10" x 24' 10"	16' 10" x 40' 10"	18' 10" x 58' 10"
24" Wall	16' 4" x 16' 4"	16' 4" x 26' 4"	18' 4" x 42' 4"	20' 4" x 60' 4"
<b>Gallons</b>				
6" Wall	323	716	1,580	2,786
12" Wall	705	1,528	3,321	5,805
18" Wall	1,146	2,436	5,222	9,055
24" Wall	1,645	3,441	7,283	12,537



# HDT THROW N' GO SELF RISING BERM

Secondary Spill Containment Berms



## Ordering information

HDT part number

NSN

On GSA Contract

<b>Fabric</b>	Polyester	
Weight	8 oz/yd <sup>2</sup>	270 g/m <sup>2</sup>
Thickness	36 mils min	0.91 mm mils
<b>Weight</b>	30.0+_ 2 oz/yd <sup>2</sup>	1020+_ 70 g/m <sup>2</sup>
<b>Tear Strength (Tongue D751B)</b>	120/120 lb min	534/534 N min
<b>Breaking Yield Strength (ASTM D 751, Grab Tensile, Proced.)</b>	625/600 lb min	2780/2670 N min
<b>Low Temperature (ASTM D 2136)</b>	Pass at -40°F/°C	
<b>Dimensional Stability (ASTM D 1204, 212°F- 1 hr)</b>	2.5% max each direction	
<b>Adhesion – Heat Sealed Seam (ASTM D 751, Dielectric Weld)</b>	25 lb/2 in min	111 N/5 cm min
<b>Bursting Strength (ASTM D 751, Ball Tip)</b>	1000 lb min	4450 N
<b>Hydrostatic Resistance (ASTM D 751, Method A)</b>	800 psi min	540 N/sq cm min
<b>Blocking Resistance (ASTM D 751, 180°F / 82°C)</b>	#2 rating max	
<b>UV Resistance</b>	8000 hrs	
<b>Puncture Resistance (ASTM D 4833)</b>	220 lb min	1110 N min

Products, product specifications and data are subject to change without notice to improve reliability, function, and/or design. Please contact Customer Service at 800.969.8527 for the most up-to-date product information.

## HDT Expeditionary Systems, Inc.

30500 Aurora Road, Suite 100

Solon, OH 44139 USA

P 800.969.8527 / 216.HDT.6111

sales@hdtglobal.com

Revision 2 03-20 01-01-10-0466